


# CHEMICAL NAME

Diethylenetriaminomethylmethyldiethoxysilane Synonym: N-(methyldiethoxysilylmethyl)diethylenetriamine N-[N'-(2-aminoethyl)aminoethyl]-aminomethyl-methyldiethoxysilane

# CHEMICAL STRUCTURE



#### INTRODUCTION

SiSiB® PC1353 is an organofunctional silane possessing three reactive amino groups and hydrolyzable ethoxysilyl groups. Due to the nature of its amino group, this substance reacts as a strong base. The silane hydrolyzes autocatalytically in the presence of moisture (ethanol is released) to form silanols, which can then react with themselves to produce siloxanes or can bind to inorganic substrates. As a bifunctional organosilane, it can also interact with numerous organic polymers and thus function as a molecular bridge (adhesion promoter, surface modifier) between organic and inorganic substrates.

SiSiB® PC1353 is a clear to straw liquid with a slight amine-like odor. It is soluble in alcohols, ketones, esters and aliphatic and aromatic hydrocarbon solvents.

The close proximity of the nitrogen atom to the silicon atom can accelerate hydrolysis reaction compared to (amino-propyl)silanes.

### APPLICATIONS

SiSiB® PC1353 can be used as an adhesion promoter in sealants, adhesives and coatings.

SiSiB® PC1353 can be used as a surface modifier for fillers.

SiSiB® PC1353 can be used in the production of silyl-modified polymers which serve as

Power Chemical IS09001 IS014001 certificated Copyright© 2009 Power Chemical Corporation Ltd. SiSiB® is a registered trademark of PCC. For more knowledge regarding organosilanes, you may visit www.SiSiB.com or www.PCC.asia



# SiSiB<sup>®</sup> PC1353 SILANE

binders in adhesives and sealants.

# TYPICAL PHYSICAL PROPERTIES

CAS No.	N/A
EINECS No.	N/A
Formula	$C_{10}H_{27}N_3O_2Si$
Molecular Weight	249.43
Boiling Point	N/A°C [760mmHg]
Flash Point	N/A°C
Color and Appearance	Clear to straw liquid
Density <sub>25/25°C</sub>	N/A
Refractive Index	N/A [25°C]
Purity:	Min.95.0%

# PACKING AND STORAGE

SiSiB® PC1353 is supplied in 200Kg steel drum or 1000Kg IBC container.

In the unopened original container SiSiB® PC1353 has a shelf life of one year in a dry and cool place.

### Notes

All information in the leaflet is based on our present knowledge and experience. We reserve the right to make any changes according to technological progress or further developments. Performance of the product described herein should be verified by testing.

We specifically disclaim any other express or implied warranty of fitness for a particular purpose or merchantability. We disclaim liability for any incidental or consequential damages.

Please send all technical questions concerning quality and product safety to: silanes@SiSiB.com.

# Power Chemical ISO9001 ISO14001 certificated

Copyright© 2009 Power Chemical Corporation Ltd. SiSiB® is a registered trademark of PCC. For more knowledge regarding organosilanes, you may visit www.SiSiB.com or www.PCC.asia