

# SiSiB® PC1711 SILANE

- 1 -

## CHEMICAL NAME

(N-phenylamino) methyltriethoxysilane, Anilinomethyltriethoxysilane

## CHEMICAL STRUCTURE

$$\begin{array}{c|c} H & OC_2H_5 \\ \hline \\ N & CH_2 & Si \\ \hline \\ OC_2H_5 \end{array}$$

### INTRODUCTION

SiSiB® PC1711 is a novel alpha silane. The close proximity of the nitrogen atom to the silicon atom can accelerate hydrolysis reaction compared to (amino-propyl)silanes.

## TYPICAL PHYSICAL PROPERTIES

CAS No.	3473-76-5
EINECS No.	N.A.
Formula	C <sub>13</sub> H <sub>23</sub> O <sub>3</sub> NSi
Molecular Weight	269.42
Boiling Point	136°C [4mmHg]
Flash Point	>110°C
Color and Appearance	Colorless to yellowish clear liquid
Density <sub>25/25°C</sub>	1.00
Refractive Index	1.485 [25°C]
Min. Purity	97.0%

## APPLICATIONS

SiSiB® PC1711 can be used in the production of silyl modified polymers which serve as binders in adhesives and sealants.

Power Chemical
IS09001 IS014001 certificated

Copyright© 2009 Power Chemical Corporation Ltd. SiSiB® is a registered trademark of PCC. For more knowledge regarding organosilanes, you may visit www.SiSiB.com or www.PCC.asia



## SiSiB® PC1711 SILANE

- 2. -

SiSiB® PC1711 also can be used as a crosslinker, water scavenger and adhesion promoter in silane-crosslinking formulations, such as adhesives, sealants and coatings.

SiSiB® PC1711 can be used as surface modifier for fillers (like glass, metal oxides, aluminum hydroxide, kaolin, wollastonite, mica) and pigments.

### PACKING AND STORAGE

SiSiB® PC1711 is supplied in 20Kg plastic drum, 180Kg steel drum or 900Kg IBC container.

In the unopened original container SiSiB® PC1800 has a shelf life of one year in a dry and cool place.

### Notes

All information in the leaflet is based on our present knowledge and experience. We reserve the right to make any changes according to technological progress or further developments. Performance of the product described herein should be verified by testing.

We specifically disclaim any other express or implied warranty of fitness for a particular purpose or merchantability. We disclaim liability for any incidental or consequential damages.

Please send all technical questions concerning quality and product safety to: silanes@SiSiB.com.

